

CHING-suprALVITE-primer SAD 182-HS VA P










Intended use

Low-solvent, diffusion-tight, active primer with barrier protection for steel and hot-dip galvanized steel with and without old coatings.

Application

Chemical plants, pipe bridges, catenary support, lattice towers, transformer substations, transmission towers, and others.

General information

	Color shades	Oxide yellow, red-brown as well as other colors on request				
	Gloss	mat				
	Stirring / Dilution	Stir the product mechanically before each use. Ready to use after adding hardener. Dilute with CHING-Thinner S 08 if necessary.				
	Spraying	Viscosity [DIN 4]	Thinner [%]	Nozzle [mm]	Pressure [bar]	
	Cup gun	50 - 70 s	5 - 10	1,5 - 2,5	4 - 5	
	Airless (Airmix)	Delivery form	≤ 3	0,31 - 0,51	120 -200	
	Brush application	Delivery form				
	Roller application	Delivery form (minimum layer thicknesses have to be expected)				
	Flow application	n.a.				
	Substrate preparation	according to DIN EN ISO 12944-4; surface clean, dry, free of dust, salt, oil and grease as well as free of adhesion-reducing substances (e.g. corrosion products)				
	Drying time¹	Temperature	Dust-dry	Grip resistant	Mech. resilient	Recoatable²
	at 60 µm	NC 23/50	1 h	2 h	4 h	4 h ³
¹ Based on delivery viscosity! Humidity has a decisive influence on drying! ² with itself (not normally required for top and final coats, except possibly for minimum coat thicknesses) ³ with suitable subsequent coating, e.g. CHING-suprALVITE top coat (SAD 00 VA P)						



**Viscosity
delivery form**

500 - 600 mPas



**Other
values**

Density [g/cm ³]	Solids [Weight. %]	Solid volume [%] [cm ³ /kg]		Efficiency ¹ [m ² /kg]
1,4 ± 0,1	70 ± 3	54 ± 3	380 ± 20	6,4
WFF	DFT ² [µm]	Consume [g/m ²]	VOC-content [g/l] (± 20)	Temperature resistance ³
1,8	60 - 80	150 ± 20	420	70°C

These values are imputed values that may vary depending on the color shade and application.
Drying times are correspondingly longer for thicker layers.
The drying times are shortened by forced drying.

¹ ± 0,5 for 60 µm dry layer thickness (depending on shade)

² With layer thicknesses > - µm bubbles may form!

³ Dry heat



Notes

- **Storage**
18 months (in unopened original container. Store cool but frost protected!)
- **Processing conditions**
 - ❖ The air and object temperature should be at +10°C to +45°C (optimally at 15-35 °C) and the relative humidity at max. 80 %. The surface temperature of the parts to be coated must be at least 3 °C above the dew point of the surrounding air during application.
 - ❖ Sufficient supply and exhaust air must be provided.