

## CHING-HIGH-SOLID-micaceous iron primer RWE-GB-9-S-3009

### Intended use

Zinc-free, micaceous iron-containing 1C-high-solid-primer as direct coating for steel and galvanized steel with or without old coating.

### Application

Initial coating as well as repair coating for overhead line pylons, transformer stations, etc.

### General information

	<b>Color shades</b>	approx. RAL 3009				
	<b>Gloss</b>	mat				
	<b>Stirring / Dilution</b>	Stir the product mechanically before each use. Ready to use after adding hardener. Dilute with CHING-Thinner DD 02 if necessary.				
	<b>Spraying</b>	<b>Viscosity [DIN 4]</b>	<b>Thinner [%]</b>	<b>Nozzle [mm]</b>	<b>Pressure [bar]</b>	
	Cup gun	30-50 s	4 - 8	1,5 - 2,5	4 - 5	
	Airless (Airmix)	Delivery Form	≤ 3	0,31 - 0,51	120 - 200	
	<b>Brush application</b>	Delivery Form				
	<b>Roller application</b>	Delivery form (not recommended for corrosion protection work due to possible blistering and crater formation and expected minimum layer thicknesses)				
	<b>Flow application</b>	n.a.				
	<b>Substrate preparation</b>	according to DIN EN ISO 12944-4 or RWE-specification; surface clean, dry, free of dust, salt, oil and grease as well as free of adhesion-reducing substances (e.g. corrosion products)				
	<b>Drying time<sup>1</sup></b>	<b>Temperature</b>	<b>Dust-dry</b>	<b>Grip resistant</b>	<b>Mech. resilient</b>	<b>Recoatable<sup>2</sup></b>
	at 80 µm	NC 23/50	1 h	12 h	36 h	24 h <sup>3</sup>
<p><sup>1</sup> Based on delivery viscosity! Humidity has a decisive influence on drying!</p> <p><sup>2</sup> with itself (not normally required for top and final coats, except possibly for minimum coat thicknesses)</p> <p><sup>3</sup> with suitable subsequent coating, e.g. RWE-DB-11-S-7033</p>						



## Viscosity delivery form

700 - 780 mPas



## Other values

Density [g/cm <sup>3</sup> ]	Solids [Weight. %]	Solid volume [%] [cm <sup>3</sup> /kg]		Efficiency <sup>1</sup> [m <sup>2</sup> /kg]
1,5 ± 0,1	79,4 ± 3	63 ± 3	410 ± 20	5,1
WFF	DFT <sup>2</sup> [µm]	Consume [g/m <sup>2</sup> ]	VOC-content [g/l] (± 20)	Temperature resistance <sup>3</sup>
1,6	80	195 ± 20	318	80°C

These values are imputed values that may vary depending on the color shade and application.  
Drying times are correspondingly longer for thicker layers.  
The drying times are shortened by forced drying.

<sup>1</sup> ± 0,5 for 80 µm dry layer thickness (depending on shade)

<sup>2</sup> With layer thicknesses > - µm bubbles may form!

<sup>3</sup> Dry heat



## Notes

- **Storage**  
18 months (in unopened original container. Store cool but frost protected!)
- **Processing conditions**
  - ❖ The air and object temperature should be at +5°C to +40°C (optimally at 15-35 °C) and the relative humidity at max. 80 %. The surface temperature of the parts to be coated must be at least 3 °C above the dew point of the surrounding air during application.
  - ❖ Sufficient supply and exhaust air must be provided.