

CHING-EP-High-Solid-MIOX-Intermediate-/Top coat 695.12-15

Intended use

2C-EP High-Solid-micaceous iron-intermediate or top coat with high resistance for steel structures in heavy-duty corrosion protection according to TL/TP-KOR-Stahlbauten, Appendix E - Sheet 95.

Application

Bridge construction, airport buildings, warehouses, parking garages, chemical plants, sign gantries, engineering structures, industrial and hall construction, tank facilities, waste incineration plants, power plants, etc.

General information

	Color shades	Grey DB 702, grey DB 703, grey DB 704, green DB 601			
	Gloss	mat			
	Mixing ratio	Hardener	per weight [Paint : Hardener]	per volume [Paint : Hardener]	
		Hardener M 052	100 : 7,5	100 : 15	
	Pot life	approx. ≥ 6 h	NC 23°C/50% Can be re-diluted within this period if necessary.		
	Stirring / Dilution	Stir the product mechanically before each use. Ready to use after adding hardener. Dilute with Thinner 695.150 if necessary.			
	Spraying	Viscosity [DIN 4]	Thinner [%]	Nozzle [mm]	Pressure [bar]
	Cup gun	40 - 70 s	5 - 10	1,5 - 2,5	3 - 5
	Airless (Airmix)	Delivery form	≤ 5	0,31 - 0,51	140 - 200
	Brush application	Delivery form			
	Roller application	Delivery form (multiple application is recommended due to structure formation and minimum layer thicknesses)			
	Flow application	n.a.			
	Substrate preparation	according to DIN EN ISO 12944-4; Steel: qualified primer and/or intermediate coating. Surface clean, dry and free of dust, salt, oil and grease. Galvanized steel: swept			



**Viscosity
delivery form**

800 - 1400 mPas



Drying time¹

at 80 µm

Temperature

NC 23/50

Dust-dry

≤ 2 h

**Grip
resistant**

≤ 16 h

**Mech.
resilient**

-

Recoatable²

≥ 8 h³

¹ Based on delivery viscosity! Humidity has a decisive influence on drying!

² with itself (not normally required for top and final coats, except possibly for minimum coat thicknesses)

³ with suitable subsequent coating, e.g. 2C-EP-Intermediate and 2C-PUR-Top coat according to sheet 95, 87 or Blatt 97



**Other
values**

Density
[g/cm³]

1,9 ± 0,1

Solids
[Weight. %]

87 ± 3

Solid volume
[%]

73 ± 3

[cm³/kg]

370 ± 20

Efficiency¹
[m²/kg]

4,7

WFF

1,4

DFT²
[µm]

80 - 150

Consume
[g/m²]

210 ± 20

VOC-content
[g/l] (± 20)

290

**Temperature
resistance³**

120°C

These values are imputed values that may vary depending on the color shade and application.
Drying times are correspondingly longer for thicker layers.
The drying times are shortened by forced drying.

¹ ± 0,5 for 80 µm dry layer thickness (depending on shade)

² With layer thicknesses > µm bubbles may form!

³ Dry heat



Notes

- **Storage**
24 months (in unopened original container. Store cool but frost protected!)
- **Processing conditions**
 - ❖ The air and object temperature should be at +7°C to +40°C (optimally at 15-35 °C) and the relative humidity at max. 80 %. The surface temperature of the parts to be coated must be at least 3 °C above the dew point of the surrounding air during application.
 - ❖ Sufficient supply and exhaust air must be provided.