

CHING-HYDRO-EP-MICA-Intermediate coating HEM 33











Intended use

Water-based, thick-layer, fast-drying 2C-EP-intermediate coat for heavy corrosion protection.

Application

Metal and mechanical engineering, industrial halls, airport buildings, warehouses, multi-storey car parks, chemical plants, pipe bridges, power stations, bridge constructions, etc.

General information

	Color shades	Lightgrey, grey, sand yellow, red brown, other colors on request			
	Gloss	mat			
	Mixing ratio	Hardener	per weight [Paint : Hardener]	per volume [Paint : Hardener]	
		Hardener HM 115 W	100 : 6	100 : 9	
	Pot life	approx. 2 h	NC 23°C/50% End of pot life not visible! Exceeding the pot life causes a reduction of technological values.		
	Stirring / Dilution	Stir the product mechanically before each use. Ready to use after adding hardener. When mechanically stirring in the hardener, the viscosity will increase temporarily. After adding the hardener and adjusting the processing viscosity, allow the mixture to degas for at least 10 minutes. Dilute with deion. Water if necessary.			
	Spraying	Viscosity [DIN 4]	Thinner [%]	Nozzle [mm]	Pressure [bar]
		Cup gun	40 - 50 s	10 - 15	1,5 - 2,5
	Airless (Airmix)	Delivery form	≤ 5	0,28 - 0,45	120 - 140
	Brush application	Delivery form			
	Roller application	Delivery form (multiple application is recommended due to structure formation and minimum layer thicknesses)			
	Flow application	n.a.			
	Substrate preparation	according to DIN EN ISO 12944-4; qualified primer, clean, dry, free of dust, salt, rust, oil and grease. For direct coating on zinc, aluminium, stainless steel: sweep-blasting according to DIN EN ISO 12944-4			



Viscosity delivery form

750 ± 150 mPas



Drying time¹

at 80 - 100 µm

Temperature

NC 23/50

Dust-dry

45 min.

Grip resistant

1,5 h

Mech. resilient

4 h

Recoatable²

1,5 h
4 h³

¹ Based on delivery viscosity! Humidity has a decisive influence on drying!

² with itself (not normally required for top and final coats, except possibly for minimum coat thicknesses)

³ with suitable subsequent coating e.g. CHING-HYDROVERSAL-top coat HV 43/47 as well as CHING-HYDRO-PUR-top coat HAD 43/47



Other values

Density
[g/cm³]

1,35 ± 0,1

Solids
[Weight. %]

63 ± 3

Solid volume
[%]

51 ± 3

Solid volume
[cm³/kg]

370 ± 20

Efficiency¹
[m²/kg]

4,6

WFF

1,9

DFT²
[µm]

80 - 120

Consume
[g/m²]

210 ± 20

VOC-content
[g/l] (± 20)

70

Temperature resistance³

120°C

These values are imputed values that may vary depending on the color shade and application. Drying times are correspondingly longer for thicker layers. The drying times are shortened by forced drying.

¹ ± 0,5 for 80 µm dry layer thickness (depending on shade)

² With layer thicknesses > - µm bubbles may form!

³ Dry heat



Notes

- **Storage**

18 months (in unopened original container. Store cool but frost protected!)

- **Processing conditions**

- ❖ The air and object temperature should be at +10°C to +40°C (optimally at 15-35 °C) and the relative humidity at max. 80 %. The surface temperature of the parts to be coated must be at least 3 °C above the dew point of the surrounding air during application.

- ❖ Sufficient supply and exhaust air must be provided.

- ❖ Experience has shown that the coating system is suitable for vapor phase drying and for operating temperatures of transformers, whereby the specified layer thickness must not exceed by more than double!

- ❖

- ❖ The equipments (e.g. spray gun, stirring unit, etc.) should be cleaned with water (tap water) immediately after use. The sooner the cleaning work is one, the better the cleaning effect. Dried material can be cleaned with CHING-Thinner EM 01.